

Plants: Emerging as Nanofactories towards Facile Route in Synthesis of Nanoparticles

Syed Baker¹, Devaraju Rakshith¹, Kumara Shanthamma Kavitha¹, Parthasarathy Santosh², Holalu Umopathy Kavitha¹, Yashavantha Rao¹, Sreedharamurthy Satish^{1*}

¹Herbal Drug Technological Laboratory, Department of Studies in Microbiology, University of Mysore, Manasagangotri, Mysore 570 006 Karnataka, India

²Plant Biotechnology Division, Unit of Central Coffee Research Institute, Coffee Board, Manasagangotri, Mysore 570 006 Karnataka, India

ARTICLE INFO

Article Type:

Review

Article History:

Received: 14 Dec. 2012

Revised: 18 Jan. 2013

Accepted: 23 Jan. 2013

ePublished: 23 Apr. 2013

Keywords:

Biosynthesis

Nanoparticles

Plants

ABSTRACT

Plant mediated nanoparticles' synthesis has led to a remarkable progress via unfolding a green synthesis protocol towards nanoparticles' synthesis. It seems to have drawn quite an unequivocal attention with a view of reformulating the novel strategies as alternatives for popular conventional methods. Hence, the present review summarizes the literature reported thus far and envisions towards plants as emerging sources of nanofactories.

Introduction

Nanotechnology is an interdisciplinary area of science which has been burgeoning interest across the globe with huge momentum to usher in forming nano revolution. An important area in nanotechnology deals with the synthesis of nanoparticles which has encountered immense progress due to innumerable applications in recent decades.¹ Nanoparticles are particles less than 100 nm in diameter that exhibit new and enhanced size-dependent properties compared to its bulk material.² The recent development and implementation of advance technologies have emerged the nano-revolution which provides the tools and technology as platforms for the investigation of biological entities which offer inspiration models for bio-assembled components toward synthesis of nanoparticles. Biosynthesis of nanoparticles is a type of bottom up approach which employs a biological system or its components for the formation of nanoparticles, where the main reaction is reduction of raw metal into nanoparticles. The process of biological route is due to metal tolerance of biological entities.³ Biological entities in synthesis of nanoparticles may vary from simple prokaryotic bacteria to eukaryotes such as fungi and plants. Compared to microorganisms, plants have better advantages wherein plant mediated synthesis is a one-step protocol towards synthesis whereas microorganisms during the course of

time may lose their ability to synthesize nanoparticles due to mutations. Further preservation of microorganisms and maintenance of cultures in active form are very laborious and time consuming. While in plants it is easy and safe with one step protocol towards synthesis; hence research on plants has expanded rapidly.^{4,5} The use of plants in synthesis of nanoparticles has become one of the popular alternatives for conventional methods. In recent years, epoch research on plants has gone through the remarkable progress with current upsurge in plant research in synthesis of nanoparticles with controlled size and shape. It is a well-known natural phenomenon of heavy metal tolerance by plants which has resulted in phytomining and phytoremediation. Thus, these unique properties of metal tolerance by plants have been exploited with respect to nanoparticles' synthesis.⁶ Plant mediated synthesis of nanoparticles is conferred due to the presence of biomolecules such as proteins, amino acids, vitamins, polysaccharides, polyphenols, terpenoids, and organic acids such as citrates etc. present in the plants as their phyto chemicals. Apart from mediating the synthesis, these molecules also stabilize the nanoparticles formed with desired size and shape. Studies have indicated that biomolecules not only play a role in reducing the ions to the nanosize, but also play an important role in the capping of nanoparticles.^{7,8}

*Corresponding author: Sreedharamurthy Satish, Email: satish.micro {at} gmail.com

Plant mediated biosynthesis of nanoparticles

The first report of the plant employed in the synthesis of nanoparticles is attributed to *Medicago sativa* (alfalfa) which was capable of synthesizing gold and silver nanoparticles.⁹ Since then, more attention has been scattered on plants. Table 1 represents myriad plant species capable of synthesizing nanoparticles. Most of the studies confer the production of nanoparticles by plants that were known to be stable than nanoparticles synthesized by microorganisms.⁶ The production of nanoparticles by plants relays on various factors among which, type of processing with optimized parameters is very much essential towards synthesis of nanoparticles such as growing plant in a media incorporated with raw material for the synthesis of nanoparticles, use of dried powdered plant material which is employed in the synthesis of plant material, drying plant material and evaluating nanoparticles synthesis, and employing fruits and flowers in the synthesis of nanoparticles. These different types of processing are known to influence nanoparticles' formation which has been reported in the various literature. When *Pelargonium graveolens* was evaluated for synthesis, reduction of the auric chloride nearly completed within 60 min and the particles' size ranged between 20–40 nm with predominant decahedral and icosahedral in shape. The study also highlighted that functional groups such as positive amino groups, sulfhydryl groups and carboxylic groups were responsible for formation of nanoparticles.¹⁰ Similarly, green unripe *Carica papaya* L fruits upon challenging with 1 mM aqueous solution of silver nitrate, resulted in synthesis of silver nanoparticles within 4 hours of incubation which was confirmed with absorption of spectra of silver nanoparticles formed in the reaction media at 450 nm, which was later confirmed by the characteristic peaks observed in the XRD. The structural view under the scanning electron microscope with average size of the particles synthesized was around 15 nm.¹¹ Similarly, *Cinnamon zeylanicum* bark extract upon evaluation for synthesis resulted in cubic and hexagonal silver nanocrystals with size ranging between 31–40 nm.¹² *Magnolia kobus*, upon evaluation, was capable of producing stable silver nanoparticles with average particle size ranging from 15 to 500 nm, extracellularly. The study also conferred that the rate of synthesis of the nanoparticles was related to the reaction and incubation temperature. They reported that increased temperature levels allowed nanoparticle growth at a faster rate. Moreover, by increasing the temperature and leaf broth concentrations, size of nanoparticles was reduced. Fourier transformed infrared spectroscopy (FTIR) analysis has shown that gold nanoparticles produced by *Magnolia kobus* extract were surrounded by proteins and other biomolecules such as terpenoids having functional groups of amines, aldehydes, carboxylic acid, and alcohols which play a vital role in synthesis of nanoparticles.¹³ It was also reported that phyllanthin extract synthesized

Table 1. Synthesis of nanoparticles using plants

Silver nanoparticles synthesizing plants	
<i>Acalypha indica</i> ¹⁴	<i>Euphorbia hirta</i> ²⁹
<i>Artocarpus Heterophyllus</i> ¹⁵	<i>Ficus bengalensis</i> ³⁰
<i>Boswellia ovalifoliolata</i> ¹⁶	<i>Fissidens minutus</i> ³¹
<i>Brassica juncea</i> ¹⁷	<i>Gliricidia sepium</i> ³²
<i>Cardiospermum helicacabum</i> ¹⁸	Honey ³³
<i>Cassia fistula</i> ¹⁹	<i>Ipomoea aquatic</i> ³⁴
<i>Cassia occidentalis</i> ²⁰	<i>Moringa oleifera</i> ³⁵
<i>Catharanthus roseus</i> ²¹	<i>Nelumbo nucifera</i> ³⁶
<i>Citrus Sinensis</i> ²²	<i>Opuntia ficus-indica</i> ³⁷
<i>Clerodendrum inerme</i> ²³	<i>Parthenium hysterophorus</i> ³⁸
<i>Cochlospermum gossypium</i> ²⁴	<i>Syzygium cumini</i> ³⁹
<i>Coriandrum Sativum</i> ²⁵	<i>Tanacetum vulgare</i> ⁴⁰
<i>Datura metel</i> ²⁶	<i>Tribulus terrestris</i> ⁴¹
<i>Desmodium triflorum</i> ²⁷	<i>Trichoderma koningii</i> ⁴²
<i>Eucalyptus hybrid</i> ²⁸	<i>Zea mays</i> ⁴³
Gold nanoparticles synthesizing plants	
<i>Camellia sinensis</i> ⁴⁴	<i>Psidium guajava</i> ⁵⁰
<i>Coriandrum sativum</i> ⁴⁵	<i>Scutellaria barbata</i> ⁵¹
<i>Cymbopogon flexuosus</i> ⁴⁶	<i>Syzygium aromaticum</i> ⁵²
<i>Momordica charantia</i> ⁴⁷	<i>Tamarindus indica</i> ⁵³
<i>Mucuna pruriens</i> ⁴⁸	<i>Terminalia catappa</i> ⁵⁴
<i>Ocimum basilicum</i> ⁴⁹	
Gold and Silver nanoparticles synthesizing plants	
<i>Aloe vera</i> ⁵⁵	<i>Emblica officianalis</i> ⁵⁹
<i>Azadirachta indica</i> ⁵⁶	<i>Emblica officinalis</i> ⁶⁰
<i>Apiin (henna leaves)</i> ⁵⁷	<i>Murraya koenigii</i> ⁶¹
<i>Cinnamomum camphora</i> ⁵⁸	

anisotropic gold and spherical–quasi-spherical silver nanoparticles by reducing aqueous chloroauric acid and silver nitrate solution at room temperature. The size and shape of the nanoparticles can be controlled by varying the concentration of phyllanthin extract to tune their optical properties in the near-infrared region of the electromagnetic spectrum. The case of low concentration of the extract with gold chloroaurate offers a slow reduction rate along with the aid of electron-donating group containing the extract leading to formation of hexagonal or triangular-shaped gold nanoparticles.⁵⁷ *Camellia sinensis* extract was evaluated to synthesize gold nanoparticles and silver nanostructures in aqueous solution. The study conferred biomolecules present in *Camellia sinensis* extract which were responsible for production and stabilization of silver and gold nanoparticles, suggested that caffeine and theophylline present in tea extracts might be responsible for catalysis and synthesis of nanoparticles. Black tea leaf extract challenged with silver nitrate and gold chloro aurate resulted in the production of polydispersed silver and gold

nanoparticles which were found to be stable. The study also reports polyphenols and flavonoids were responsible for synthesis of nanoparticles.⁴⁴ Furthermore, Hudlikara *et al.* reported synthesis of titanium dioxide nanoparticles with 0.3% aqueous extract prepared from latex of *Jatropha curcas* L, with nanoparticles' size within the range of 25–100 nm. Fourier Transform Infrared Spectroscopy was performed to find the role of curcain, cyclic peptides, namely curcacycline A and curcacycline B as possible reducing and capping agents.⁶² The leaf extract of *Ocimum sanctum* rapidly synthesized silver nanoparticles with a size range of 4–30 nm within 8 min of reaction time. It was reported that *Ocimum sanctum* leaf extract could reduce silver ions into crystalline silver nanoparticles ranging 4–30 nm within 8 min of reaction time. These nanoparticles were stable due to the presence of proteins which may act as a capping agent. Biosynthesized silver nanoparticles have also displayed strong antimicrobial activity against *Escherichia coli* and *Staphylococcus aureus*.⁶³ A green synthesis route for the production of silver nanoparticles using methanol extract from *Solanum xanthocarpum* berry was reported; the reduction was rapid within 25 min at 45°C. The synthesized silver nanoparticles were characterized using UV–Visible spectrophotometry, powdered X-ray diffraction, and transmission electron microscopy. The nanoparticles were found to be about 10 nm in size, mono-dispersed in nature, and spherical in shape.⁶⁴ Hence, the brief reports discussed above have given an insight towards plant mediated nanoparticles' synthesis wherein the biomolecules present in plants were held responsible for synthesis of nanoparticles due to which there is an burgeoning interest across the globe for evaluating plants for synthesis of nanoparticles and thus such processes form a safer alternative and eco friendly. At the same time, few studies also confer and report that various parameters attribute to the size control synthesis of nanoparticles.

Factors influencing the nanoparticles' synthesis

Several factors such as temperature, pH, concentration of extracts, concentration of raw material, etc. influence the reduction process of metal ions into the metal nanoparticles.

pH

The pH value of the medium influences the size of nanoparticles under formation in both extracts and living plants. Studies by Gardea Torresdey *et al.* on alfalfa biomass indicated that pH is an important factor in the bioformation of colloidal gold.⁶⁵ Similarly, formation of gold nanoparticles was evaluated using biomass of *Avena sativa*. The study also reported that the size of gold nanoparticles can be controlled by altering the pH of medium.⁶⁶

Temperature

One of the most interesting aspects of nanoparticles' biosynthesis is the fact that this process occurs at ambient

temperature. However, the temperature of the reaction medium is a critical factor that determines the nature of nanoparticles formed. When *Cymbopogon flexuosus* was evaluated to produce gold nanoparticles at higher temperatures, the percentage of gold nanotriangles relative to spherical particles were significantly reduced at high temperature, whereas low temperature mostly promoted nano triangle formation.⁶⁷

Biomolecules

Among the various categories of compounds synthesized by plants such as phytochemicals, primary and secondary metabolites are known as important natural resources for the synthesis of metallic nanoparticles.⁶⁸ A large number of papers have been published on the biosynthesis of nanoparticles using the phytochemicals contained in the extracts of a number of plant species. On the contrary, little has been understood about this process in living plants. Beattie and Haverkamp recently investigated gold and silver nanoparticles formation within the tissues of *Brassica juncea* with the aim of clarifying the mechanisms of nanoparticle formation and a couple of experimental observations were recorded. It was found that the sites of the most abundant reduction of metal salts to nanoparticles were the chloroplasts in which high reducing sugars (glucose and fructose) are responsible for biofabrication of silver and gold nanoparticles.⁶⁹

Purification of nanoparticles

Purification of nanoparticles is carried out by an array of techniques such as centrifugation, which forms a base for nanoparticle separation wherein nanoparticles which are denser than a liquid settle down due to the gravitational force.⁷⁰ Usually ultra centrifugation techniques are widely used to separate the nanoparticles based on the size and shape. Apart from centrifugation technique, chromatographic based separation is followed in order to separate nanoparticles based on the coefficients between mobile phase and stationary phase. Use of HPLC has been reported in the various literature from which ion exchange chromatographic separation is followed during which, based on the charge, nanoparticles are separated from the mixture.⁷¹ The efficient separation process for nanoparticles are attributed to one or more techniques for instance extraction of nanoparticles based on their solubilities in two different miscible liquid phases usually water and organic solvents, which is followed by chromatographic techniques or electrophoresis techniques. Electrophoresis techniques employ the uniform electric charge for separation wherein charge particles migrate towards the opposite electrode based on the size and shape of the nanoparticles.⁷² Separation of nanoparticles is an important aspect for the application of nanoparticles.⁷³

Applications of plant mediated nanoparticles

Green principle based synthesized nanoparticles are known to have immense applications in the field of medicine and biology when compared to the nanoparticles synthesized

by chemical protocols which involves the use of harsh solvents or surfactants. The reducing agents in chemical synthesis are known to generate hazardous waste but in green principle based nanoparticles, no use of hazardous chemicals instead of phyto biomolecules present in the plants form the reducing agents and stabilizing agents which typically increase the biomedical applications of green principle based nanoparticles. *In vivo* applications of the plant mediated nanoparticles are more superior compared to the chemically synthesized nanoparticles due to the fact that the biomolecules such as amino acid, proteins, salts and so forth, which are responsible for synthesis and stability of nanoparticles upon evaluation at *in vivo* condition, cause irreversible agglomeration due to chemical similarity among the cellular growth components which are required for cell growth and proliferation.⁷⁴ Some studies also suggest that use of plant mediated synthesized nanoparticles are more ideal and compatible for their use in nanomedicine because of their stability in various biological media.⁷⁵ Plant mediated nanoparticles are evaluated as potent antimicrobial agents against various human and phytopathogenic microorganisms. Biosynthesized silver nanoparticles using stem bark extracts of *Boswellia* were evaluated against a panel of pathogenic microorganisms viz *Proteus*, *Pseudomonas*, *Klebsiella*, *Bacillus* and *E.coli* species of bacteria and *Aspergillus*, *Fusarium*, *Curvularia* and *Rhizopus* species of fungi.⁷⁶

Nanoparticles synthesized via plants, are also employed in physio-chemical applications; for instance, Indium oxide nanoparticles using *Aloe vera* plant displayed a strong photoluminescence in the UV region. The strong emissions of indium oxide are attributed to the radioactive recombination of electron occupying oxygen vacancies with a photo-excited hole. Thus, the study has conferred the use of plant mediated nanoparticles as fluorescence labels towards detection of various analytes.⁷⁷

Characterization of plant mediated nanoparticles and their applications

Characterization of nanoparticles is one of the important aspects which are carried out by microscopic techniques such as scanning electron microscopy, transmission electron microscopy and atomic force microscopy. These microscopic techniques are employed to reveal the size and shape of nanoparticles as described in the literature reported pertaining to nanoparticle synthesis. Initially, preliminary confirmation of nanoparticles is carried out by UV-Visible spectroscopic technique which represents different characteristic peaks at absorptions at electromagnetic spectrum which is due to the surface plasma resonance of the nanoparticles formed. Further characterization of nanoparticles is carried out with analytical hyphenated techniques such as fourier transform infrared (FTIR) spectroscopy which measures infrared intensity versus wavelength of light which results

in determination of associated biomolecules of plants with nanoparticles. Apart from these techniques, XRD and Raman spectroscopy are widely used to characterize the nanoparticles formed.⁷⁸ The fate of nanoparticles mainly depends on the characterization which reveals the size, shape and nature of the nanoparticles.

Future prospective

Plant mediated nanoparticles' synthesis protocols have an upsurge in recent past as a safe, eco-friendly and an alternative for most popular conventional methods which are bound with various implications. Promoting biosynthesis of nanoparticles can influence the commercial applications of these nanoparticles in the field of pharmaceuticals and other medical sciences which are limited factors for nanoparticles synthesized via conventional methods. The present review summarizes the literature, which confers plants as emerging source for nanoparticle synthesis, which can be advantageous over other biological processes such as microorganism by eliminating the elaborate process of maintaining microorganism cultures which can lose its potential to synthesize due to mutations. At the same time, harvesting the endangered plant species may pose a risk among the plant diversity which can form a major impact. Hence, in this regard new technologies offer isolation of biomolecules responsible for synthesis of nanoparticles and challenge synthesizing the nanoparticles forming template based synthesis of nanoparticles. In the near future, a thorough detailed study will be valuable enough to give a clear description of biomolecules mediating the synthesis of nanoparticles which will influence the rate of synthesis and improve properties of nanoparticles with stability.

Conclusion

Increasing awareness towards green chemistry and biological processes has led to desire and influenced process which is environment-friendly for the synthesis of non-toxic nanoparticles. Owing to the rich biodiversity of plants, mediated nanoparticle synthesis has become a subject of interest across the globe with different plant species being rapidly explored and evaluated for synthesizing of nanoparticles. Nanoparticles synthesized via plants have been used for human benefit. The mechanism of plants in synthesizing nanoparticles is yet to be completely elucidated. Additional research in this area can further increase the potential in biosynthesis of nanoparticles. Harvest of endangered species of plants may pose a risk to the biodiversity of plant kingdom which should be looked forward in the near future. Future research on plant mediated biological synthesis of nanoparticles with unique optoelectronics, physicochemical and electronic properties are of great importance for applications in the areas of chemistry, electronics, medicine and agriculture.

Acknowledgments

Authors are pleased to thank University Grant Commission (UGC) for their financial support and Department of Studies in Microbiology, University of Mysore for providing facilities.

Ethical issues

The authors declare no ethical issues.

Competing interests

The authors report no competing interests.

References

- Cheon J, Horace G. Inorganic nanoparticles for biological sensing, imaging and therapeutics. *J Mater Chem* **2009**;19: 6249-50.
- Baker S, Satish S. Endophytes: Toward a vision in synthesis of nanoparticles for future therapeutic agents. *J Bio-Inorg Hybd Nanomat* **2012**;1:1-11.
- Li S, Shen Y, Xie A, Yu X, Qui L, Zhang L, Zhang Q. Green synthesis of silver nanoparticles using *Capsicum annum* L. extract. *Green Chem* **2007**;9:852-8.
- Mandal D, Bolander ME, Mukhopadhyay D, Sarkar G, Mukherjee P. The use of microorganisms for synthesis of metal nanoparticles and their application. *Appl Microbiol Biotechnol* **2006**;69:485-92.
- Cui D, Gao H. Advance and prospect of bionanomaterials. *Biotechnol Progr* **2003**;19:683.
- Iravani S. Green synthesis of metal nanoparticles using plants. *Green Chem* **2011**;13:2638-50.
- Collera Zuniga O, Jimenez FG, Gordillo RM. Comparative study of carotenoid composition in three Mexican varieties of *Capsicum annum* L. *Food Chem* **2005**;90:109-14.
- Jagadeesh BH, Prabha TN, Srinivasan K. Improved shelf life of bell capsicum fruits by manipulation of the activities of glycosidases through heat. *Indian J Plant Physiol* **2004**;9:164-8.
- Gardea-Torresdey JL, Gomez E, Peralta-Videa JR, Parsons JG, Troiani H, Jose-Yacaman M. Alfalfa sprouts: A natural source for the synthesis of silver nanoparticles. *Langmuir* **2003**;19:1357-61.
- Shankar SS, Ahmad A, Pasricha R, Sastry M. Bioreduction of chloroaurate ions by geranium leaves and its endophytic fungus yields gold nanoparticles of different shapes. *J Mater Chem* **2003**;13:1822-6.
- Jain D, Hemant Kumar D, Kachhwaha S, Kothari SL. Synthesis of plant-mediated silver nanoparticles using Papaya fruit extract and evaluation of their anti microbial activities. *Dig J Nano Biostruct* **2009**;4:723-7.
- Sathishkumar M, Sneha K, Won SW, Cho CW, Kim S, Yun YS. Cinnamon zeylanicum bark extract and powder mediated green synthesis of nano-crystalline silver particles and its bactericidal activity. *Colloids Surf B* **2009**;73:332-8.
- Song JY, Kim BS. Biological synthesis of bimetallic Au/Ag nanoparticles using Persimmon (*Diopyros kaki*) leaf extract. *Korean J Chem Eng* **2008**;25:808-11.
- Krishnaraj C, Jagan EG, Rajasekar S, Selvakumar P, Kalaichelvan PT, Mohan, N. Synthesis of silver nanoparticles using *Acalypha indica* leaf extracts and its antibacterial activity against water borne pathogens. *Colloids Surf B* **2010**;76:50-6.
- Thirumurugan A, Neethu AT, Jaiganesh R, Gobikrishnan S. Biological reduction of silver nanoparticles using plant leaf extracts and its effect on increased antimicrobial activity against clinically isolated organism. *Der Pharma Chemica* **2010**;2: 279-84.
- Ankana S, Prasad KV, Elumalai EK, Savithamma N. Production of biogenic silver nanoparticles using *Boswellia ovalifoliolata* stem bark. *Dig J Nano-mater Biostruct* **2010**;5:369-72.
- Haverkamp RG, Marshall AT. The mechanism of metal nanoparticle formation in plants: Limits on accumulation. *J Nanopart Res* **2008**;1:1453-63.
- Mitra B, Vishnudas D, Sant BS, Annamalai A. Green synthesis and characterization of silver nanoparticles by aqueous Leaf extracts of *Cardiospermum helicacabum* L. *Drug Inven Today* **2012**;4:340-4.
- Lin L, Wang W, Huang J, Li Q, Sun D, Yang X, Wang H, He N, Wang Y. Nature factory of silver nanowires: Plant mediated synthesis using broth of *Cassia fistula* leaf. *Chem Eng J* **2010**;162:852-8.
- Arya V, Yadav S, Kumar S, Yadav JP. Antimicrobial activity of *Cassia occidentalis* L (Leaf) against various human pathogenic microbes. *Life Sci Med Res* **2010**;9:1-11.
- Mukunthan KS, Elumalai EK, Trupti NP, Ramachandra VM. *Catharanthus roseus*: A natural source for the synthesis of silver nanoparticles. *Asian Pac J Trop Biomed* **2011**;11:270-4.
- Kaviya S, Santhanalakshmi J, Viswanathan B, Muthumary J, Srinivasan K. Biosynthesis of silver nanoparticles using citrus sinensis peel extract and its antibacterial activity. *Spectrochim Acta A Mol Biomol Spectrosc* **2011**;79:594-8.
- Farooqui MDA, Chauhan PS, Krishnamoorthy P, Shaik J. Extraction of silver nanoparticle from the leaf extracts of *Clerodendrum inerme*. *Dig J Nano-mater Biostruct* **2010**;5: 543-9.
- Kora AJ, Sashidhar RB, Arunachalam J. Gum kondagogu (*Cochlospermum gossypium*): A template for the green synthesis and stabilization of silver nanoparticles with antibacterial application. *J Carbohydr Polym* **2010**;82:670-9.
- Sathyavathi R, Krishna MB, Rao SV, Saritha R, Rao DN. Biosynthesis of silver nanoparticle using *Coriandrum sativum* leaf extract and their application in nonlinear. *Optics Adv Sci Lett* **2010**;3:1-6.
- Kesharwani J, Yoon KY, Hwang J, Rai M. Phytofabrication of silver nanoparticles by leaf extract of *Datura metel*: Hypothetical mechanism involved in

- synthesis. *J Bionanosci* **2009**;3:39-44.
27. Ahmad N, Sharma S, Singh VN, Shamsi SF, Fatma A, Mehta BR. Biosynthesis of silver nanoparticle from *Desmodium triflorum*: A novel approach towards weed utilization. *Biotechnol Res Int* **2011**;2011: 454090.
28. Dubey M, Bhaduria S, Kushwah BS. Green synthesis of nanosilver particles from extract of *Eucalyptus hybrida* (safeda) leaf. *Dig J Nano-mater Biostruct* **2009**;4:537-43.
29. Manopriya M, Karunai B, Selvi JA, Paul J. Green synthesis of silver nanoparticles from the leaf extracts of *Euphorbia hirta* and *Nerium indicum*. *Dig J Nano-mater Biostruct* **2011**;6:869-77.
30. Saxena A, Tripathi RM, Zafar F, Singh . Green synthesis of silver nanoparticles using aqueous solution of *Ficus benghalensis* leaf extract and characterization of their antibacterial activity. *Materials Letters* **2012**;67:91-4.
31. Srivastava AA, Kulkarni AP, Harpale PM, Zunjarrao RS. Plant mediated synthesis of silver nanoparticles using a bryophyte: *Fissidens minutus* and its anti-microbial activity. *Int J Eng Sci Tech* **2011**;3:417-21.
32. Rajesh WR, Jaya RL, Niranjan SK, Vijay DM, Sahebrao BK. Photosynthesis of silver nanoparticle using *Gliricidia sepium*. *Curr Nanosci* **2009**;5:117-22.
33. Philip D. Honey mediated green synthesis of gold nanoparticles. *Spectrochim Acta Part A* **2009**;73:650-3.
34. Fazaludeen MF, Manickam C, Ashankyta Ibraheem MA, Ahmed MQ, Beg QZ. Synthesis and characterizations of gold nanoparticles by *Justicia gendarussa burm F* leaf extract. *J Microbiol Biotech Res* **2012**;2:23-34.
35. Prasad TN, Elumalai E. Biofabrication of Ag nanoparticles using *Moringa oleifera* leaf extract and their antimicrobial activity. *Asian Pac J Trop Biomed* **2011**;2011:439-42.
36. Santhoshkumar T, Rahuman AA, Rajakumar G, Marimuthu S, Bagavan A, Jayaseelan, C, Zahir AA, Elango G, Kamaraj C. Synthesis of silver nanoparticles using *Nelumbo nucifera* leaf extract and its larvicidal activity against malaria and filariasis vectors. *Parasitol Res* **2010**;108:693-702.
37. Gade A, Gaikwad S, Tiwari V, Yadav A, Ingle A, Rai M. Biofabrication of silver nanoparticle by *Opuntia ficus-indica*: In vitro antibacterial activity and study of the mechanism involved in the synthesis. *Curr Nanosci* **2010**;6:370-5.
38. Parashar V, Parashar R, Sharma B, Pandey AC. *Parthenium* leaf extract mediated synthesis of silver nanoparticles: A novel approach towards weed utilization. *Dig J Nano Biostruct* **2009**;4:45-50.
39. Kumar V, Yadav SC, Yadav SK. *Syzygium cumini* leaf and seed extract mediated biosynthesis of silver nanoparticles and their characterization. *J Chem Technol Biotechnol* **2010**;85:1301-9.
40. Dubey SP, Lahtinen M, Sillanpaa M. Tansy fruit mediated greener synthesis of silver and gold nanoparticles. *Process Biochem* **2010**;45:1065-71.
41. Gopinath D, Mubarak Ali, Priyadarshini S, Priyadharshini NM, Thajuddin N, Velusamy P. Biosynthesis of silver nanoparticles from *Tribulus terrestris* and its antimicrobial activity: A novel biological approach. *Colloids Surf B* **2012**;96:69-74.
42. Maliszewska I, Aniszkievicz L, Sadowski Z. Synthesis and properties of silver nanoparticles for biomedical applications. *Acta Phys Pol A* **2009**;116:163-5.
43. Duran N, Marcato PD, Alves OL, De Souza GIH, Esposito E. Mechanistic aspects of biosynthesis of silver nanoparticles by several *Fusarium oxysporum* strains. *J Nanobiotechnol* **2005**;3:8-14.
44. Vilchis-Nestora AR, Sanchez-Mendieta V, Camacho-Lopez MA, Gomez-Espinosaa RM, Camacho-Lopez MA, Arenas-Alatorre J. Solventless synthesis and optical properties of Au and Ag nanoparticles using *Camellia sinensis* extract. *Mater Lett* **2008**;62:3103-05.
45. Narayanan KB, Sakthivel N. Coriander leaf mediated biosynthesis of gold nanoparticle. *Mater Lett* **2008**;62:4588-90.
46. Shankar SS, Rai A, Ankamwar B, Sing A, Ahmad A, Sastry M. Biological synthesis of triangular gold nanoprisms. *Nat Mater* **2004**;3:482-8.
47. Pandey S, Oza G, Mewada A, Sharon M. Green synthesis of highly stable gold nanoparticles using *Momordica charantia* as nano fabricator. *Arch Appl Sci Res* **2012**;4:1135-41.
48. Arulkumar S, Sabesan M. Biosynthesis and characterization of gold nanoparticle using antiparkinsonian drug *Mucuna pruriens* plant extract. *Int J Res Pharm Sci* **2010**;4:417-20.
49. Singhal GS, Riju B, Ranjan A, Rajendra SP. Ecofriendly biosynthesis of gold nanoparticles using medicinally important *Ocimum basilicum* leaf extract. *Adv Sci Eng Med* **2012**;4:62-6.
50. Raghunandan D, Basavaraja S, Mahesh B, Balaji S, Manjunath SY, Venkataraman A. Biosynthesis of stable polycrystalline gold nanoparticles from microwave-exposed aqueous extracellular anti-malignant guava (*Psidium guajava*) leaf extract. *Nanobiotechnol* **2009**;5:34-41.
51. Wang Y, He X, Wang K, Zhang X, Tan W. Barbated Skull cup herb extract-mediated biosynthesis of gold nanoparticles and its primary application in electrochemistry. *Colloids Surf B* **2009**;73:75-9.
52. Deshpande R, Bedre MD, Basavaraja S, Sawle B, Manjunath SY, Venkataraman A. A rapid biosynthesis of irregular shaped gold nanoparticles from macerated aqueous extracellular dried clove buds (*Syzygium aromaticum*) solution. *Colloids Surf B* **2010**;79:235-40.
53. Ankamwar B, Chaudhary M, Murali S. Gold nanotriangles biologically synthesized using tamarind leaf extract and potential application in vapor sensing. *Synth React Inorg Met Org Nano Met Chem* **2005**;35:19-26.
54. Ankamwar B. Biosynthesis of gold nanoparticles (green-gold) using leaf extract of *Terminalia catappa*. *E J Chem* **2010**;7:1334-9.

55. Chandran SP, Chaudhary M, Pasricha R, Ahmad A, Sastry M. Synthesis of gold nanotriangles and silver nanoparticles using Aloe vera plant extract. *Biotechnol Prog* **2006**;22:577-83.
56. Shankar SS, Rai A, Ahmad A, Sastry M. Rapid synthesis of Au, Ag, and bimetallic Au core-Ag shell nanoparticles using neem (*Azadirachta indica*) leaf broth. *J Colloid Interface Sci* **2004**;275:496-502.
57. Kasthuri J, Veerapandian S, Rajendiran N. Biological synthesis of silver and gold nanoparticles using apiin as reducing agent. *Colloids Surf A* **2009**;68:55-60.
58. Huang J, Li Q, Sun D, Lu Y, Su Y, Yang X. Biosynthesis of silver and gold nanoparticles by novel sundried *Cinnamomum camphora* leaf. *Nanotechnology* **2007**;18:105104.
59. Ankamwar B, Damle C, Ahmad A, Sastry M. Biosynthesis of gold and silver nanoparticles using *Embllica officinalis* fruit extract, their phase transfer and transmetallation in an organic solution. *J Nanosci Nanotechnol* **2005**;5:1665-71.
60. Ramezani N, Ehsanfar Z, Shamsa F, Amin G, Shahverdi HR, Monsef-Esfahanic HR, Shamsaie A, Dolatabadi-Bazaz R, Shahverdi AR. Screening of medicinal plant methanol extracts for the synthesis of gold nanoparticles by their reducing potential. *Naturforsch B* **2008**;63:903-8.
61. Philip D, Unni C, Aromal SA, Vidhu VK. *Murraya koenigii* leaf-assisted rapid green synthesis of silver and gold nanoparticles. *Spectrochim Acta A Mol Biomol Spectrosc* **2011**;78:899-904.
62. Hudlikar M, Joglekar S, Dhaygude M, Kodam K. Green synthesis of TiO₂nanoparticles by using aqueous extract of *Jatropha curcas* L. latex. *Materials Lett* **2012**;75:196-9.
63. Singhal G, Bhavesh R, Kasariya K, Sharma AR, Singh RP. Biosynthesis of silver nanoparticles using *Ocimum sanctum* (tulsi) leaf extract and screening its antimicrobial activity. *J Nanopart Res* **2011**;13:2981-8.
64. Amin M, Anwar F, Saeed Ashraf Janjua MR, Iqbal MA, Rashid U. Green synthesis of silver nanoparticles through reduction with *Solanum xanthocarpum* L. berry extract: Characterization, antimicrobial and urease inhibitory activities against *helicobacter pylori*. *Int J Mol Sci* **2012**;13:9923-41.
65. Gardea-Torresdey JL, Tiemann KJ, Gamez G, Dokken K, Pingitore NE. Recovery of gold (III) by alfalfa biomass and binding characterization using x-ray microfluorescence. *Adv Environ Res* **1999**;3:83-93.
66. Armendariz V, Herrera I, Peralta-Videa JR, Jose-Yacaman M, Troiani H, Santiago P, Gardea-Torresdey JL. Size controlled gold nanoparticle formation by *Avena sativa* biomass: Use of plants in nanobiotechnology. *J Nanopart Res* **2004**;6:377-82.
67. Rai A, Singh A, Ahmad A, Sastry M. Role of halide ions and temperature on the morphology of biologically synthesized gold nanotriangles. *Langmuir* **2006**;22:736-41.
68. Park Y, Hong YN, Weyers A, Kim YS, Linhardt RJ. Polysaccharides and phytochemicals: A natural reservoir for the green synthesis of gold and silver nanoparticles. *IET Nanobiotechnol* **2011**;5:69-78.
69. Haverkamp RG, Agterveld DV, Marshall AT. Pick your carats: Nanoparticles of gold-silver copper alloy produced in vivo. *J Nanopart Res* **2007**;9:697-700.
70. Brakke, MK. Density gradient centrifugation and its application to plant viruses. *Advances in Virus Research* New York: Academic Press; **1961**.
71. Jimenez VL, Leopold MC, Mazzitelli C, Jorgenson JW, Murray RW. HPLC of monolayer-protected gold nanoclusters. *Anal Chem* **2003**;75:199-206.
72. Hanauer M, Pierrat S, Zins I, Lotz A, Sonnichsen C. Separation of nanoparticles by gel electrophoresis according to size-and shape. *Nano Lett* **2007**;7:2881-5.
73. Kowalczyk B, Lagzi I, Grzybowski BA. Nanoseparations: Strategies for size and/or shape-selective purification of nanoparticles. *Curr Opin Colloid In* **2011**;16:135-48.
74. White GV, Kerscher P, Brown RM, Morella JD, McAllister W, Dean D, Christopher LK. Green synthesis of robust, biocompatible silver nanoparticles using garlic extract. *J Nanomater* **2012**;2012: 730746.
75. Shukla R, Nune SK, Chanda N, Katti K, Mekapothula S, Kulkarni RR, Welshons WV, Kannan R, Katti KV. Soybeans as a phytochemical reservoir for the production and stabilization of biocompatible gold nanoparticles. *Small* **2008**;4:1425-36.
76. Savithramma N, Rao ML, Rukmini K, Devi PS. Antimicrobial activity of silver nanoparticles synthesized by using medicinal plants. *Int J Chem Tech Res* **2011**;3:1394-402.
77. Maensiri S, Laokul P, Klinkaewnarong J, Phokha S, Promarak V, Seraphin S. Indium oxide (In₂O₃) nanoparticles using Aloe vera plant extract: Synthesis and optical properties. *J Optoelectron Adv Mater* **2008**;10:161-5.
78. Kumar V, Yadav SK. Plant-mediated synthesis of silver and gold nanoparticles and their applications. *J Chem Technol Biotechnol* **2009**;84:151-7.